






































Composition Composición	100% Solution Dyed Acrylic 100% Acrílico tintado en masa	Uses Usos
Weight Peso	450 g/m <sup>2</sup> 13.3 oz/yd <sup>2</sup>	 
Width Ancho	160 cm 63"	 
Rapport	80x117 cm 31.5x46.1"	 
Length of Roll Longitud de las piezas	30 ml 32.8 yd	 
Finish Acabado	 Water Repellent Hidrófugo  Anti-Stain Antimanchas  Eco-Shield No PFAs	
Colour Fastness to Light Solidez del color a la luz	7-8/8 UNE EN ISO 105-B02:2014	Qualities Cualidades
Colour Fastness to Artificial Weathering Solidez del color a la interperie artificial	7-8/8 UNE EN ISO 105-B04:1998	 
Colour Fastness to Rubbing Solidez del color al frote	4-5/5 UNE EN ISO 105-X12:2016	 
Colour Fastness to Chlorinated Water Solidez del color al agua clorada	5/5 UNE EN ISO 105-E03:2010	 
Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/1996	 
Spray Test	4/5 UNE EN ISO 4920	 
Tear Resistance Resistencia al desgarro	Warp Urdimbre 130 N Weft Trama 170 N UNE EN ISO 13937-3:2001	  
Slippage Resistance Deslizamiento a la costura	Warp Urdimbre 5,0 mm 0.19" Weft Trama 3,0 mm 0.12" UNE EN ISO 13936-2:2004	  
Tensile Strength Resistencia a la tracción	Warp Urdimbre 1800 N Weft Trama 2400 N UNE EN ISO 13934-1:2013	  
Resistance to Pilling Resistencia al pilling	3-4/5 UNE EN ISO 12945-2:2001	Optional Finishes Acabados opcionales
Abrasion Resistance (Martindale) Resistencia a la abrasión (Martindale)	35000 UNE EN ISO 12497-2:2016	 WATERPROOF IMPERMEABLE
Shrinkage to Washing Encogimiento al lavado	Warp Urdimbre -1,5% Weft Trama 0% UNE EN ISO 5077:2007	 EXTRA SOFTNESS SUAVIDAD EXTRA
Flammability Inflamabilidad	UNE 1021 PART 1 BS 5852-0 Cigarette Test Cal 117, NFPA 260	
Cleaning Instructions Manutención	    	Waterproof and flame retardant finishes: Recommended for cushions and upholstery only. Acabados Waterproof y FR: Recomendado únicamente para cojines y tapicería.

Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%



The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations. La garantía Agora cubre un anormal deterioro del tejido debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y químicos de la atmósfera en general, siempre y cuando el tejido haya sido instalado, utilizado y mantenido correctamente. La garantía no cubre los trabajos de instalación del distribuidor. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.

