






















Composition Composición	100% Solution Dyed Acrylic 100% Acrílico tintado en masa	Uses Usos
Structure Estructura	Warp Urdimbre 31 h/cm (Nm 2/34) Weft Trama 14 h/cm (Nm 2/34) UNE-EN 1049-2	 
Weight Peso	310 g/m ² 9.1 oz/y ²	 
Width Ancho	153 cm 60"	 
Length of Roll Longitud de las piezas	50 m 54.7 yd	
Finish Acabado	Water repellent Resin-coated Eco-Shield Hidrofugado Resinado No PFAS	
Colour Fastness to Light Solidez del color a la luz	7-8/8 UNE EN ISO 105-B02:2014	
Colour Fastness to Artificial Weathering Solidez del color a la intemperie artificial	7-8/8 UNE EN ISO 105-B04:1998	Qualities Cualidades
Colour Fastness to Rubbing Solidez del color al frote	4-5/5 UNE EN ISO 105-X12:2016	 
Colour Fastness to Chlorinated Water Solidez del color al agua clorada	5/5 UNE EN ISO 105-E03:2010	WATER REPELLENT HIDROFUGO STAIN RESISTANT ANTIMANCHAS
Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/1996	 
Water Repellency (Spray test) Repelencia al agua	100 (5) UNE EN ISO 24920	MOULD RESISTANT ANTIMOHO UV PROTECT PROTECCIÓN UV
Water Column Columna de agua	650 mm 25,5" UNE EN ISO 20811	 
Tear Resistance Resistencia al desgarro	Warp Urdimbre 49 N Weft Trama 32 N UNE EN ISO 13937-3:2001	UV RESISTANT RESISTENCIA UV DURABLE DURADERO
Slippage Resistance Deslizamiento a la costura	Warp Urdimbre 5,0 mm 0.19" Weft Trama 3,0 mm 0.12" UNE EN ISO 13936-2:2004	 
Tensile Strength Resistencia a la tracción	Warp Urdimbre 1800 N Weft Trama 860 N UNE EN ISO 13934-1:2013	EASY TO CLEAN FÁCIL DE LIMPIAR BREATHABLE TRANSPIRABLE
Shrinkage to Washing Encogimiento al lavado	Warp Urdimbre -1,5% Weft Trama 0% UNE EN ISO 5077:2007	
Flammability Inflamabilidad	UNE 1021 PART 1 BS 5852-0 Cigarette Test Cal 117, NFPA 260	
Cleaning Instructions Manutención	    	

Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%



The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations. La garantía Agora cubre un anormal deterioro del tejido debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y químicos de la atmósfera en general, siempre y cuando el tejido haya sido instalado, utilizado y mantenido correctamente. La garantía no cubre los trabajos de instalación del distribuidor. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.

