

























| | | |
|--|---|--|
| Composition Composición | 100% Solution Dyed Acrylic 100% Acrílico tintado en masa | Uses Usos |
| Structure Estructura | Warp Urdimbre 31 h/cm (Nm 2/34) Weft Trama 14 h/cm (Nm 2/34) UNE-EN 1049-2 |   |
| Weight Peso | 290 g/m ² 8.5 oz/y ² |   |
| Width Ancho | 160 cm 63" |   |
| Length of Roll Longitud de las piezas | 50 m 54.7 yd |   |
| Finish Acabado |  Water Repellent Hidrófugo  Eco-Shield No PFAs | |
| Colour Fastness to Light Solidez del color a la luz | 7-8/8 UNE EN ISO 105-B02:2014 | |
| Colour Fastness to Artificial Weathering Solidez del color a la intemperie artificial | 7-8/8 UNE EN ISO 105-B04:1998 | Qualities Cualidades |
| Colour Fastness to Rubbing Solidez del color al frote | 4-5/5 UNE EN ISO 105-X12:2016 |  WATER REPELLENT HIDROFUGO  STAIN RESISTANT ANTIMANCHAS |
| Colour Fastness to Chlorinated Water Solidez del color al agua clorada | 5/5 UNE EN ISO 105-E03:2010 |  MOULD RESISTANT ANTIMOHO  UV PROTECT PROTECCIÓN UV |
| Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF | 50+ AZ/NZS 4399/1996 |  UV RESISTANT RESISTENCIA UV  DURABLE DURADERO |
| Water Repellency (Spray test) Repelencia al agua | 100 (5) UNE EN ISO 24920 |  EASY TO CLEAN FÁCIL DE LIMPIAR  BREATHABLE TRANSPIRABLE |
| Water Column Columna de agua | 360 mm 14" UNE EN ISO 20811 | |
| Tear Resistance Resistencia al desgarro | Warp Urdimbre 82 N Weft Trama 33 N UNE EN ISO 13937-3:2001 | |
| Slippage Resistance Deslizamiento a la costura | Warp Urdimbre 5,0 mm 0.19" Weft Trama 3,0 mm 0.12" UNE EN ISO 13936-2:2004 | |
| Tensile Strength Resistencia a la tracción | Warp Urdimbre 1700 N Weft Trama 960 N UNE EN ISO 13934-1:2013 | |
| Shrinkage to Washing Encogimiento al lavado | Warp Urdimbre -1,5% Weft Trama 0% UNE EN ISO 5077:2007 | |
| Flammability Inflamabilidad | UNE 1021 PART 1 BS 5852-0 Cigarette Test Cal 117, NFPA 260 | |
| Cleaning Instructions Manutención |      | |

Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%



The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations. La garantía Agora cubre un anormal deterioro del tejido debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y químicos de la atmósfera en general, siempre y cuando el tejido haya sido instalado, utilizado y mantenido correctamente. La garantía no cubre los trabajos de instalación del distribuidor. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.

