

Technical Data ALGAE

Composition Composición	100% Solution Dyed Acrylic 100% Acrílico tintado en masa		Uses Usos	
Weight Peso	780 g/m ² 23 oz/y ²		 	
Width Ancho	160 cm 63"		 	
Rapport	70x80 cm 31x31.5"		 	
Lenght of Roll Longitud de las piezas	30 ml 32.8 yd			
Finish Acabado	 Water Repellent Hidrófugo  Anti-Stain Antimanchas  Eco-Shield No PFAs  Ultra Soft Ultra Suave		Qualities Cualidades	
Colour Fastness to Light Solidez del color a la luz	7-8/8 UNE EN ISO 105-B02:2014 Método 2		 	
Colour Fastness to Artificial Weathering Solidez del color a la interperie artificial	7/8 UNE EN ISO 105-B04:1997		 	
Colour Fastness to Rubbing Solidez del color al frote	4-5/5 UNE EN ISO 105-X12:2016		 	
Colour Fastness to Chlorinated Water Solidez del color al agua clorada	5/5 UNE EN ISO 105-E03:2010		 	
Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/2017		 	
Spray Test	4/5 EN ISO 4920:2012		 	
Tear Resistance Resistencia al desgarro	Warp Urdimbre 371 N Weft Trama 356 N UNE EN ISO 13937-2:2000		  	
Slippage Resistance Deslizamiento a la costura	Warp Urdimbre 1,5 N Weft Trama 2 N UNE EN ISO 13936-2:2004 - 6mm		  	
Tensile Strenght Resistencia a la tracción	Warp Urdimbre 3,6 N Weft Trama 4,1 N UNE EN ISO 13934-1:2013		  	
Resistance to Pilling Resistencia al pilling	3-4/5 UNE EN ISO 12945-2		  	
Abrasion Resistance (Martindale) Resistencia a la abrasión (Martindale)	18000 UNE EN ISO 12497-2:2016		  	
Shrinkage to Washing Encogimiento al lavado	Warp Urdimbre -2% Weft Trama -1% UNE EN ISO 5077:2008		  	
Flammability Inflamabilidad	UNE 1021 PART 1 BS 5852-0 Cigarette Test Cal 117, NFPA 260		  	
Cleaning Instructions Manutención	    		 WATERPROOF IMPERMEABLE Waterproof finish: Recommended for cushions and upholstery only. Always use the lamination face inside. Do not expose the coated side to sun or any atmospheric agents. Acabado Waterproof: Recomendado únicamente para cojines y tapicería. Siempre utilizar la cara laminada en el interior y no exponerla al sol o a las inclemencias del clima.	

Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%