

Technical Data MIMBRES

Composition Composición	100% Solution Dyed Acrylic 100% Acrílico tintado en masa	Uses Usos
Weight Peso	865 g/m ² 25.5 oz/y ²	 
Width Ancho	160 cm 63"	 
Rapport	2,1x2,7 cm 0.8x1"	 
Lenght of Roll Longitud de las piezas	20 ml 21.8 yd	
Finish Acabado	 Water Repellent Hidrófugo  Anti-Stain Antimanchas  Eco-Shield No PFAs  Ultra Soft Ultra Suave	Qualities Cualidades
Colour Fastness to Light Solidez del color a la luz	7-8/8 UNE EN ISO 105-B02:2014 Método 2	 
Colour Fastness to Artificial Weathering Solidez del color a la interperie artificial	7/8 UNE EN ISO 105-B04:1997	 
Colour Fastness to Rubbing Solidez del color al frote	4-5/5 UNE EN ISO 105-X12:2016	 
Colour Fastness to Chlorinated Water Solidez del color al agua clorada	5/5 UNE EN ISO 105-E03:2010	 
Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/2017	
Spray Test	3-4/5 EN ISO 4920:2012	
Tear Resistance Resistencia al desgarro	Warp Urdimbre 176 N Weft Trama 289 N UNE EN ISO 13937-2:2000	
Slippage Resistance Deslizamiento a la costura	Warp Urdimbre 1,5 N Weft Trama 1,6 N UNE EN ISO 13936-2:2004 - 6mm	
Tensile Strenght Resistencia a la tracción	Warp Urdimbre 2,1 N Weft Trama 2,7 N UNE EN ISO 13934-1:2013	  
Resistance to Pilling Resistencia al pilling	5/5 UNE EN ISO 12945-2	
Abrasion Resistance (Martindale) Resistencia a la abrasión (Martindale)	20000 UNE EN ISO 12497-2:2016	Optional Finishes Acabados opcionales
Shrinkage to Washing Encogimiento al lavado	Warp Urdimbre -2% Weft Trama -1% UNE EN ISO 5077:2008	 WATERPROOF IMPERMEABLE
Flammability Inflamabilidad	UNE 1021 PART 1 BS 5852-0 Cigarette Test Cal 117, NFPA 260	Waterproof finish: Recommended for cushions and upholstery only. Always use the lamination face inside. Do not expose the coated side to sun or any atmospheric agents. Acabado Waterproof: Recomendado únicamente para cojines y tapicería. Siempre utilizar la cara laminada en el interior y no exponerla al sol o a las inclemencias del clima.
Cleaning Instructions Manutención	    	

Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%