

Composition Composición	100% Solution Dyed Acrylic 100% Acrílico tintado en masa	Uses Usos
Weight Peso	420 g/m ² 12.4 oz/y ²	       
Width Ancho	160 cm 63"	
Rapport	5,5 cm 2.2"	
Lenght of Roll Longitud de las piezas	30 ml 32.8 yd	
Finish Acabado	 Water Repellent Hidrófugo  Anti-Stain Antimanchas	
Colour Fastness to Light Solidez del color a la luz	7-8/8 UNE EN ISO 105-B02:2014	Qualities Cualidades
Colour Fastness to Artificial Weathering Solidez del color a la interperie artificial	7-8/8 UNE EN ISO 105-B04:1998	
Colour Fastness to Rubbing Solidez del color al frote	4/5 UNE EN ISO 105-X12:2016	
Colour Fastness to Chlorinated Water Solidez del color al agua clorada	5/5 UNE EN ISO 105-E03:2010	
Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/1996	
Spray Test	4/5 UNE EN ISO 24920	
Tear Resistance Resistencia al desgarro	Warp Urdimbre 200 N Weft Trama 160 N UNE EN ISO 13937-3:2001	
Slippage Resistance Deslizamiento a la costura	Warp Urdimbre 5,0 mm 0.19" Weft Trama 3,0 mm 0.12" UNE EN ISO 13936-2:2004	
Tensile Strenght Resistencia a la tracción	Warp Urdimbre 1900 N Weft Trama 2100 N UNE EN ISO 13934-1:2013	
Resistance to Pilling Resistencia al pilling	3-4/5 UNE EN ISO 12945-2:2001	
Abrasion Resistance (Martindale) Resistencia a la abrasión (Martindale)	25000 UNE EN ISO 12497-2:2016	
Shrinkage to Washing Encogimiento al lavado	Warp Urdimbre -1,5% Weft Trama 0% UNE EN ISO 5077:2007	Optional Finishes Acabados opcionales
Flammability Inflamabilidad	UNE 1021 PART 1 BS 5852-0 Cigarette Test Cal 117, NFPA 260	
Cleaning Instructions Manutención	    	

Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%



The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations. La garantía Agora cubre un anormal deterioro del tejido debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y químicos de la atmósfera en general, siempre y cuando el tejido haya sido instalado, utilizado y mantenido correctamente. La garantía no cubre los trabajos de instalación del distribuidor. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.

