

Composition Composición	100% Solution Dyed Acrylic 100% Acrílico tintado en masa	Uses Usos
Weight Peso	260 g/m ² 7.7 oz/y ²	 
Width Ancho	160 cm 63"	 
Rapport	10 cm 3.9"	 
Lenght of Roll Longitud de las piezas	50 ml 54.7 yd	 
Finish Acabado	 Water Repellent Hidrófugo  Anti-Stain Antimanchas	 
Colour Fastness to Light Solidez del color a la luz	7-8/8 UNE EN ISO 105-B02:2014	Qualities Cualidades
Colour Fastness to Artificial Weathering Solidez del color a la interperie artificial	7-8/8 UNE EN ISO 105-B04:1998	
Colour Fastness to Rubbing Solidez del color al frote	4-5/5 UNE EN ISO 105-X12:2016	
Colour Fastness to Chlorinated Water Solidez del color al agua clorada	5/5 UNE EN ISO 105-E03:2010	
Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/1996	
Spray Test	5/5 UNE EN ISO 24920	  WATER REPELLENT HIDRÓFUGO STAIN RESISTANT ANTIMANCHAS
Water Column mm Columna de agua mm	180 UNE EN ISO 20811	  MOULD RESISTANT ANTIMOHO UV PROTECT PROTECCIÓN UV
Tear Resistance Resistencia al desgarro	Warp Urdimbire 170 N Weft Trama 150 N UNE EN ISO 13937-3:2001	  UV RESISTANT RESISTENCIA UV DURABLE DURADERO
Slippage Resistance Deslizamiento a la costura	Warp Urdimbire 5,0 mm 0.19" Weft Trama 3,0 mm 0.12" UNE EN ISO 13936-2:2004	  EASY TO CLEAN FÁCIL DE LIMPIAR BREATHABLE TRANSPIRABLE
Tensile Strenght Resistencia a la tracción	Warp Urdimbire 1600 N Weft Trama 800 N UNE EN ISO 13934-1:2013	  BLEACH friendly DURABLE is green
Resistance to Pilling Resistencia al pilling	4-5/5 UNE EN ISO 12945-2:2001	Optional Finishes Acabados opcionales
Abrasion Resistance (Martindale) Resistencia a la abrasión (Martindale)	20000 UNE EN ISO 12497-2:2016	
Shrinkage to Washing Encogimiento al lavado	Warp Urdimbire -1,5% Weft Trama 0% UNE EN ISO 5077:2007	
Flammability Inflamabilidad	UNE 1021 PART 1 BS 5852-0 Cigarette Test Cal 117, NFPA 260	
Cleaning Instructions Manutención	    	 WATERPROOF IMPERMEABLE
		 safe home EXTRA SOFTNESS SUAVIDAD EXTRA
		 FLAME RETARDANT IGNIFUGADO

Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%



The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations. La garantía Agora cubre un anormal deterioro del tejido debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y químicos de la atmósfera en general, siempre y cuando el tejido haya sido instalado, utilizado y mantenido correctamente. La garantía no cubre los trabajos de instalación del distribuidor. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.

