



Composition Composición	90% SDA - 10% Polyester AT 90% SDA - 10% Poliéster AT
Core Alma	Polyester Hight Tenacity Poléster Alta Tenacidad
Width Ancho	40 mm 1.6"
Weight Peso	43 g/m 0.5 oz/yd
Thickness Grosor	1,5 mm 0.06"
Finish Acabado	 Water Repellent Hidrófugo  Anti-Stain Antimanchas
Colour fastness to light Solidez a la luz	7/8 UNE EN ISO 105-B02:2014
Colour fastness to artificial weathering Solidez del color a la intemperie artificial	7-8/8 UNE-EN ISO 105-B04:1998
Colour fastness to rubbing Solidez de las tinturas al frote	4-5/5 UNE EN ISO 105-X12:2016
Colour fastness to chlorinated water Solidez de las tinturas al agua clorada	5/5 UNE EN ISO 105-E03:2010
Ultraviolet protection factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/1996
Spray test	5/5 UNE EN ISO 24920
Water column mm Columna de agua mm	100 UNE EN ISO 20811
Breaking Strength Resistencia a la rotura	3200 N UNE EN ISO 13934-1:2013
Resistance to pilling Resistencia al pilling	4/5 UNE EN ISO 12945-2:2001
Abrasion resistance (Martindale) Resistencia a la abrasión (Martindale)	20000 UNE EN ISO 12497-2:2016
Cleaning instructions Manutención	    

Uses
Usos



Qualities
Cualidades



Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%.