



Composition Composición	100% Solution Dyed Acrylic 100% Acrílico Tintado en Masa
Width Ancho	160 cm 63"
Weight Peso	290 g/m² 8.5 oz/yd²
Length of rolls Longitud de las piezas	50 m 54.7 yd
Finish Acabado	 Water Repellent Hidrófugo  Anti-Stain Antimanchas
Colour fastness to light Solidez a la luz	7-8/8 UNE EN ISO 105-B02:2014
Colour fastness to artificial weathering Solidez del color a la intemperie artificial	7-8/8 UNE-EN ISO 105-B04:1998
Colour fastness to rubbing Solidez de las tinturas al frote	4-5/5 UNE EN ISO 105-X12:2016
Colour fastness to chlorinated water Solidez de las tinturas al agua clorada	5/5 UNE EN ISO 105-E03:2010
Ultraviolet protection factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/1996
Spray test	5/5 UNE EN ISO 24920
Water column mm Columna de agua mm	360 UNE EN ISO 20811
Tear resistance Resistencia al desgarro	Warp Urdimbre 82 N Weft Trama 33 N UNE EN ISO 13937-3:2001
Slippage resistant Deslizamiento a la costura	Warp Urdimbre 5,0 mm 0.19" Weft Trama 3,0 mm 0.12" UNE EN ISO 13936-2:2004
Tensile strength Resistencia a la tracción	Warp Urdimbre 1700 N Weft Trama 960 N UNE EN ISO 13934-1:2013
Shrinkage to washing Encogimiento al lavado	Warp Urdimbre -1'5% Weft Trama 0% UNE EN ISO 5077:2007
Cleaning instructions Manutención	    

Uses
Usos



Qualities
Calidades



Sensitive values of tolerance +/- 5%. Valores susceptibles de tolerancia de +/- 5%.